



Global Thermoset Composite Solutions

Sheet Products - Property Comparison

			MC223	NP310	NP310BW	NP310E
			Cotton (Canvas)			
			Phenolic			
PHYSICAL PROPERTIES						
Specific Gravity (0.500")		-	1.44	1.37	1.47	1.37
Rockwell Hardness (0.250" Build-up)		M Scale	105	100	100	100
Moisture Absorption (0.062")	Condition D ₁ -24/23	%	1.20	3.50	2.50	2.00
Flexural Strength (0.062")	Condition A Lengthwise / Crosswise	psi	18,000 / --	18,000 / 17,000	-- / --	17,500 / 15,000
	Condition E-1/150 T150 Lengthwise / Crosswise		-- / --	-- / --	-- / --	-- / --
Flexural Modulus (0.062")	Lengthwise / Crosswise	kpsi	-- / --	1,600 / 1,500	-- / --	1,600 / 1,500
Tensile Strength (0.125")	Lengthwise / Crosswise	psi	12,000 / --	12,000 / 9,700	43,000 / --	11,000 / 9,000
Izod Impact Strength (0.500")	Condition E-48/50 Lengthwise / Crosswise	ft-lb/in (notched)	2.00 / 1.20	3.10 / 2.70	-- / --	1.70 / 1.50
Compressive Strength (0.500")	Flatwise	psi	38,000	34,000	43,000	34,000
Bonding Strength (0.500")	Condition A	lb	1,700	2,500	1,200	1,700
	Condition D-48/50		--	2,300	--	1,700
Shear Strength (0.062")	Perpendicular	psi	13,000	14,000	--	14,000
THERMAL PROPERTIES						
Temperature Index ¹	Electrical / Mechanical	°C	115 / 125	115 / 125	-- / 150	115 / 125
Coefficient of Thermal Expansion (0.125")	X-axis / Y-axis	"/"/°Cx10 ⁻⁶	-- / --	20.0 / 22.0	-- / --	20.0 / 22.0
Flammability Rating U.L. 94 (0.062")	Condition A	Class	HB	HB	HB	HB
ELECTRICAL PROPERTIES						
Dissipation Factor (0.062")	Condition D ₁ -24/23	-	--	--	--	--
Permittivity (0.062")	Condition D ₁ -24/23	-	--	--	--	--
Breakdown Voltage (0.062")	Condition A	kV	--	20	--	40
	Condition D-48/50		--	5	--	3
Electric Strength (0.062")	Condition A	V/mil	--	400	--	550
	Condition D-48/50		--	150	--	300
Arc Resistance D495 (0.125")	Condition A	sec	--	15	--	15
Comparative Tracking Index D3638 (0.125")		V	--	155	--	--

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.
 NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.



Global Thermoset Composite Solutions

Sheet Products - Property Comparison

			NP310HT	NP310U	NP313	NP313HT
			Cotton (Canvas)			
			Phenolic		Phenolic - MoS2	
PHYSICAL PROPERTIES						
Specific Gravity (0.500")		-	1.37	1.35	1.40	1.40
Rockwell Hardness (0.250" Build-up)		M Scale	100	100	100	100
Moisture Absorption (0.062")	Condition D ₁ -24/23	%	3.40	2.00	1.95	--
Flexural Strength (0.062")	Condition A Lengthwise / Crosswise	psi	18,000 / 18,000	23,000 / 13,500	19,000 / 17,000	-- / --
	Condition E-1/150 T150 Lengthwise / Crosswise		-- / --	-- / --	-- / --	-- / --
Flexural Modulus (0.062")	Lengthwise / Crosswise	kpsi	2,500 / 2,400	900 / 1,000	1,200 / 1,000	-- / --
Tensile Strength (0.125")	Lengthwise / Crosswise	psi	-- / --	7,500 / 6,000	11,000 / 9,000	16,000 / 9,000
Izod Impact Strength (0.500")	Condition E-48/50 Lengthwise / Crosswise	ft-lb/in (notched)	2.35 / 2.02	1.50 / 1.00	1.70 / 1.40	3.50 / 2.70
Compressive Strength (0.500")	Flatwise	psi	35,000	28,000	36,000	49,000
Bonding Strength (0.500")	Condition A	lb	2,700	1,900	1,900	2,300
	Condition D-48/50		2,400	--	--	--
Shear Strength (0.062")	Perpendicular	psi	--	13,000	13,500	--
THERMAL PROPERTIES						
Temperature Index ¹	Electrical / Mechanical	°C	-- / 145	125 / 125	-- / 145	-- / 145
Coefficient of Thermal Expansion (0.125")	X-axis / Y-axis	"/"°Cx10 ⁻⁶	-- / --	20.0 / 22.0	18.0 / 24.0	10.0 / 15.0
Flammability Rating U.L. 94 (0.062")	Condition A	Class	HB	HB	HB	HB
ELECTRICAL PROPERTIES						
Dissipation Factor (0.062")	Condition D ₁ -24/23	-	--	--	--	--
Permittivity (0.062")	Condition D ₁ -24/23	-	--	--	--	--
Breakdown Voltage (0.062")	Condition A	kV	55	50	--	--
	Condition D-48/50		--	3	--	--
Electric Strength (0.062")	Condition A	V/mil	527	550	--	--
	Condition D-48/50		--	300	--	--
Arc Resistance D495 (0.125")	Condition A	sec	--	15	--	--
Comparative Tracking Index D3638 (0.125")		V	--	150	--	--

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.

NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.



Global Thermoset Composite Solutions

Sheet Products - Property Comparison

			NP315	NP318	NP319
			Cotton (Canvas)		
			Phenolic - Graphite	Phenolic	Phenolic - Graphite
PHYSICAL PROPERTIES					
Specific Gravity (0.500")		-	1.40	1.35	1.41
Rockwell Hardness (0.250" Build-up)		M Scale	90	90	100
Moisture Absorption (0.062")	Condition D ₁ -24/23	%	2.20	4.20	2.50
Flexural Strength (0.062")	Condition A Lengthwise / Crosswise	psi	19,000 / 15,000	17,000 / 14,000	20,000 / 18,000
	Condition E-1/150 T150 Lengthwise / Crosswise		-- / --	-- / --	-- / --
Flexural Modulus (0.062")	Lengthwise / Crosswise	kpsi	1,200 / 1,000	1,100 / 900	1,300 / 1,000
Tensile Strength (0.125")	Lengthwise / Crosswise	psi	10,000 / 7,000	10,000 / 6,000	11,000 / 9,000
Izod Impact Strength (0.500")	Condition E-48/50 Lengthwise / Crosswise	ft-lb/in (notched)	1.70 / 1.40	2.50 / 2.00	-- / --
Compressive Strength (0.500")	Flatwise	psi	38,000	25,000	36,000
Bonding Strength (0.500")	Condition A	lb	1,800	1,800	2,000
	Condition D-48/50		--	--	--
Shear Strength (0.062")	Perpendicular	psi	13,000	12,000	13,000
THERMAL PROPERTIES					
Temperature Index ¹	Electrical / Mechanical	°C	-- / 125	125 / 125	-- / 145
Coefficient of Thermal Expansion (0.125")	X-axis / Y-axis	"/"/°Cx10 ⁻⁶	18.0 / 24.0	-- / --	18.0 / 22.0
Flammability Rating U.L. 94 (0.062")	Condition A	Class	HB	HB	HB
ELECTRICAL PROPERTIES					
Dissipation Factor (0.062")	Condition D ₁ -24/23	-	--	--	--
Permittivity (0.062")	Condition D ₁ -24/23	-	--	--	--
Breakdown Voltage (0.062")	Condition A	kV	--	65	--
	Condition D-48/50		--	4	--
Electric Strength (0.062")	Condition A	V/mil	--	480	--
	Condition D-48/50		--	350	--
Arc Resistance D495 (0.125")	Condition A	sec	--	10	--
Comparative Tracking Index D3638 (0.125")		V	--	150	--

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.

NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

Sheet Products - Property Comparison

			MC320LE	NP320	NP320E	NP320U
			Cotton (Fine Weave Linen)			
			Phenolic			
PHYSICAL PROPERTIES						
Specific Gravity (0.500")		-	1.38	1.34	1.34	1.34
Rockwell Hardness (0.250" Build-up)		M Scale	102	100	100	95
Moisture Absorption (0.062")	Condition D ₁ -24/23	%	0.87	2.30	1.90	3.00
Flexural Strength (0.062")	Condition A Lengthwise / Crosswise	psi	24,000 / --	24,500 / 18,500	22,000 / 16,000	19,000 / 13,500
	Condition E-1/150 T150 Lengthwise / Crosswise		-- / --	-- / --	-- / --	-- / --
Flexural Modulus (0.062")	Lengthwise / Crosswise	kpsi	-- / --	1,700 / 1,300	1,600 / 1,200	1,500 / 1,100
Tensile Strength (0.125")	Lengthwise / Crosswise	psi	18,800 / --	14,000 / 10,000	13,000 / 9,000	13,000 / 9,000
Izod Impact Strength (0.500")	Condition E-48/50 Lengthwise / Crosswise	ft-lb/in (notched)	2.00 / 1.70	1.70 / 1.35	1.35 / 1.10	1.10 / 0.86
Compressive Strength (0.500")	Flatwise	psi	38,000	38,000	36,000	30,000
Bonding Strength (0.500")	Condition A	lb	1,700	2,000	1,900	1,700
	Condition D-48/50		--	--	--	--
Shear Strength (0.062")	Perpendicular	psi	14,000	13,500	13,500	12,000
THERMAL PROPERTIES						
Temperature Index ¹	Electrical / Mechanical	°C	115 / 125	115 / 125	125 / 125	115 / 125
Coefficient of Thermal Expansion (0.125")	X-axis / Y-axis	"/"/°Cx10 ⁻⁶	-- / --	18.0 / 19.0	18.0 / 19.0	20.0 / 22.0
Flammability Rating U.L. 94 (0.062")	Condition A	Class	HB	HB	HB	HB
ELECTRICAL PROPERTIES						
Dissipation Factor (0.062")	Condition D ₁ -24/23	-	0.044	0.070	0.065	0.054
Permittivity (0.062")	Condition D ₁ -24/23	-	5.30	5.80	5.50	6.60
Breakdown Voltage (0.062")	Condition A	kV	70	45	50	50
	Condition D-48/50		--	2	5	5
Electric Strength (0.062")	Condition A	V/mil	--	575	625	625
	Condition D-48/50		--	450	500	500
Arc Resistance D495 (0.125")	Condition A	sec	130	15	15	15
Comparative Tracking Index D3638 (0.125")		V	--	170	170	170

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.
NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.



Global Thermoset Composite Solutions

Sheet Products - Property Comparison

			NP322	NP324	NP325	NP329
			Cotton (Fine Weave Linen)			
			Phenolic - MoS2	Phenolic-PTFE	Phenolic - Graphite	Melamine
PHYSICAL PROPERTIES						
Specific Gravity (0.500")		-	1.39	--	1.39	1.47
Rockwell Hardness (0.250" Build-up)		M Scale	103	--	100	110
Moisture Absorption (0.062")	Condition D ₁ -24/23	%	2.40	1.19	1.50	1.80
Flexural Strength (0.062")	Condition A Lengthwise / Crosswise	psi	23,800 / 18,000	22,000 / 21,500	20,100 / 19,200	29,000 / 26,000
	Condition E-1/150 T150 Lengthwise / Crosswise		-- / --	-- / --	-- / /	-- / --
Flexural Modulus (0.062")	Lengthwise / Crosswise	kpsi	1,500 / 1,100	-- / --	1,500 / 1,100	1,800 / 1,400
Tensile Strength (0.125")	Lengthwise / Crosswise	psi	14,000 / 9,700	-- / --	13,500 / 9,500	16,000 / 9,700
Izod Impact Strength (0.500")	Condition E-48/50 Lengthwise / Crosswise	ft-lb/in (notched)	1.60 / 1.30	1.96 / 1.46	1.42 / 1.35	1.90 / 1.75
Compressive Strength (0.500")	Flatwise	psi	39,000	--	35,000	34,000
Bonding Strength (0.500")	Condition A	lb	1,900	1,370	1,900	1,900
	Condition D-48/50		--	1,250	--	--
Shear Strength (0.062")	Perpendicular	psi	14,500	--	14,500	13,000
THERMAL PROPERTIES						
Temperature Index ¹	Electrical / Mechanical	°C	130 / 130	-- / --	-- / 125	-- / 130
Coefficient of Thermal Expansion (0.125")	X-axis / Y-axis	"/"°Cx10 ⁻⁶	10.0 / 12.0	-- / --	10.0 / 12.0	18.0 / 19.0
Flammability Rating U.L. 94 (0.062")	Condition A	Class	HB	HB	HB	HB
ELECTRICAL PROPERTIES						
Dissipation Factor (0.062")	Condition D ₁ -24/23	-	--	--	--	0.050
Permittivity (0.062")	Condition D ₁ -24/23	-	--	--	--	7.00
Breakdown Voltage (0.062")	Condition A	kV	30	25	--	20
	Condition D-48/50		5	--	--	5
Electric Strength (0.062")	Condition A	V/mil	--	--	--	500
	Condition D-48/50		--	--	--	300
Arc Resistance D495 (0.125")	Condition A	sec	--	--	--	120
Comparative Tracking Index D3638 (0.125")		V	--	--	--	200

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.
 NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

Sheet Products - Property Comparison

			NP342	NP342LS
			Cotton (Fine Weave Linen)	
			Phenolic	
PHYSICAL PROPERTIES				
Specific Gravity (0.500")		-	1.35	1.35
Rockwell Hardness (0.250" Build-up)		M Scale	100	100
Moisture Absorption (0.062")	Condition D ₁ -24/23	%	1.80	--
Flexural Strength (0.062")	Condition A Lengthwise / Crosswise	psi	25,000 / 22,700	-- / --
	Condition E-1/150 T150 Lengthwise / Crosswise		-- / --	-- / --
Flexural Modulus (0.062")	Lengthwise / Crosswise	kpsi	1,700 / 1,300	-- / --
Tensile Strength (0.125")	Lengthwise / Crosswise	psi	12,700 / 10,900	-- / --
Izod Impact Strength (0.500")	Condition E-48/50 Lengthwise / Crosswise	ft-lb/in (notched)	1.60 / 1.40	-- / --
Compressive Strength (0.500")	Flatwise	psi	35,000	37,000
Bonding Strength (0.500")	Condition A	lb	1,900	--
	Condition D-48/50		--	--
Shear Strength (0.062")	Perpendicular	psi	14,000	--
THERMAL PROPERTIES				
Temperature Index ¹	Electrical / Mechanical	°C	-- / 125	125 / 125
Coefficient of Thermal Expansion (0.125")	X-axis / Y-axis	"/"/°Cx10 ⁻⁶	20.0 / 22.0	-- / --
Flammability Rating U.L. 94 (0.062")	Condition A	Class	HB	HB
ELECTRICAL PROPERTIES				
Dissipation Factor (0.062")	Condition D ₁ -24/23	-	--	--
Permittivity (0.062")	Condition D ₁ -24/23	-	--	--
Breakdown Voltage (0.062")	Condition A	kV	40	--
	Condition D-48/50		3	--
Electric Strength (0.062")	Condition A	V/mil	550	--
	Condition D-48/50		300	--
Arc Resistance D495 (0.125")	Condition A	sec	--	--
Comparative Tracking Index D3638 (0.125")		V	--	--

NOTE a: A double dash (--) indicates that the value has not been determined or is not applicable to the product.

NOTE b: All testing per ASTM D348 unless otherwise noted.

¹ NEMA LI-6: This temperature is a recommendation only and is based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.