

NP322

TECHNICAL DATA BULLETIN

GRADE: NP322

U.L. LISTED: N

DESCRIPTION: NP322 is composed of a linen substrate combined with a phenolic resin system which contains molybdenum disulfide for reduced wear and increased lubrication. Provides the same lubricity as NP313, but has better machining qualities. The mechanical strength is similar to, but slightly less than NP320. NP322 is used in applications where reduced wear is needed in non-conductive applications.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.39
Rockwell Hardness (ASTM D785)	0.250" Build-up	M Scale	103		
Moisture Absorption (ASTM D570)	Condition A	%			
	Condition D ₁ -24/23	%	2.40		
Flexural Strength (ASTM D790)	Condition A	psi	23,800 / 18,000		
	LW / CW	(Mpa)	(164.1) / (124.1)		
Flexural Modulus (ASTM D790)	Condition A	kpsi	1,500 / 1,100		
	LW / CW	(Gpa)	(10.3) / (7.6)		
Tensile Strength (ASTM D638)	Condition A	psi		14,000 / 9,700	
	LW / CW	(Mpa)		(96.5) / (66.9)	
Izod Impact Strength (ASTM D256)	Condition A	ft-lb/in			
	LW / CW	(J/cm)			
	Condition E-48/50	ft-lb/in			1.60 / 1.30
	LW / CW	(J/cm)			(0.85) / (0.69)
Compressive Strength (ASTM D695)	Condition A	psi			39,000
	Flatwise	(Mpa)			(268.9)
Bonding Strength (ASTM D229)	Condition A	lb			1,900
		(kg)			(861.8)
Shear Strength (ASTM D732)	Condition A	psi	14,500		
	Perpendicular	(Mpa)	(100.0)		

TECHNICAL DATA BULLETIN

GRADE: NP322

U.L. LISTED: N

TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Thickness Tested		
		0.0625"	0.125"	0.500"
THERMAL PROPERTIES				
Temperature Index ¹ (UL Bulletin 746b) Electrical / Mechanical	°C	130 / 130		
Coefficient of Thermal Expansion (IPC-TM 650-2.4.24) X-axis / Y-axis	" / °C x10 ⁻⁶		10.0 / 12.0	
Flammability Rating Condition A (UL Bulletin 94)	Class	HB		
ELECTRICAL PROPERTIES				
Breakdown Voltage (ASTM D149) Condition A	kVolts	30		
	Condition D-48/50	kVolts	5	

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.