

NP664

TECHNICAL DATA BULLETIN

GRADE: NP664

NEMA LI 1-1998 Grade: XPC

U.L. LISTED: N

DESCRIPTION: Low cost room temperature punching grade with mechanical and electrical properties similar to NP612. This version is made with pigment cover plies on the surface. NP664 also complies with ANSI/NEMA IM 60000-2021 Grade XPC and IEC 60893-4-1 PF CP 207.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.37
Rockwell Hardness (ASTM D785)0.250" Build-up		M Scale	90		
Moisture Absorption (ASTM D570)Condition D ₁ -24/23		%	5.50		
Flexural Strength (ASTM D790)LW / CW		psi (MPa)	26,000 / 24,000 (179.3) / (165.5)		
Flexural Modulus (ASTM D790)LW / CW		kpsi (GPa)	1,200 / 1,000 (8.3) / (6.9)		
Tensile Strength (ASTM D638)LW / CW		psi (MPa)		22,500 / 12,500 (155.1) / (86.2)	
Izod Impact Strength (ASTM D256)		Condition A	ft-lb/in (J/cm)		
		LW / CW			
		Condition E-48/50 LW / CW	ft-lb/in (J/cm)		0.67 / 0.62 (0.36) / (0.33)
Compressive Strength (ASTM D695)Flatwise		psi (MPa)			30,000 (206.8)
Bonding Strength (ASTM D229)		lb (kg)			1,100 (499.0)
Shear Strength (ASTM D732)Perpendicular		psi (MPa)	11,000 (75.8)		

TECHNICAL DATA BULLETIN

GRADE: NP664

NEMA LI 1-1998 Grade: XPC

U.L. LISTED: N

TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Thickness Tested		
		0.0625"	0.125"	0.500"
THERMAL PROPERTIES				
Temperature Index ¹ (UL Bulletin 746b) Electrical / Mechanical	°C	130 / 130		
Coefficient of Thermal Expansion (IPC-TM 650-2.4.24) X-axis / Y-axis	" / °C x10 ⁻⁶		18.0 / 20.0	
Flammability Rating Condition A (UL Bulletin 94)	Class	HB		
ELECTRICAL PROPERTIES				
Breakdown Voltage Condition A (ASTM D149)	kVolts	60		
	Condition D-48/50	kVolts	10	
Electric Strength Condition A (ASTM D149)	Volts/mil (kV/cm)	500 (196.9)		
	Condition D-48/50	Volts/mil (kV/cm)	300 (118.1)	
Arc Resistance Condition A (ASTM D495)	sec		110	
Comparative Tracking Index (ASTM D3638)	Volts		180	

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.