

P95

TECHNICAL DATA BULLETIN

GRADE: P95

NEMA LI 1-1998 Grade: --

U.L. LISTED: N

DESCRIPTION: Woven glass fabric combined with a high temperature polyimide resin system engineered to maintain excellent physical properties at 240°C. P95 has a low coefficient of thermal expansion, high mechanical strength and excellent heat resistance. P95 meets IEC 60893-3-7 PICG 301, ANSI/NEMA IM 60000-2021 Grade G-15 and IPC 4101/40 rev. E specifications.

TYPICAL PROPERTIES

		UNITS	VALUE		
			Thickness Tested		
			0.0625"	0.125"	0.500"
PHYSICAL PROPERTIES					
Specific Gravity (ASTM D792)		-			1.84
Rockwell Hardness (ASTM D785)	0.250" Build-up	M Scale	120		
Moisture Absorption (ASTM D570)	Condition D ₁ -24/23	%	0.35		
Flexural Strength (ASTM D790)	Condition A LW / CW	psi (MPa)	78,000 / 66,000 (537.8) / (455.1)		
Flexural Modulus (ASTM D790)	Condition A LW / CW	kpsi (GPa)	3,200 / 2,800 (22.1) / (19.3)		
Tensile Strength (ASTM D638)	Condition A LW / CW	psi (MPa)	48,000 / 40,000 (330.9) / (275.8)		
Izod Impact Strength (ASTM D256)	Condition A LW / CW	ft-lb/in (J/cm)			
	Condition E-48/50 LW / CW	ft-lb/in (J/cm)	11.50 / 7.50 (6.14) / (4.00)		
Compressive Strength (ASTM D695)	Condition A Flatwise	psi (MPa)	70,000 (482.6)		
Bonding Strength (ASTM D229)	Condition A	lb (kg)	1,500 (680.4)		
Shear Strength (ASTM D732)	Condition A Perpendicular	psi (MPa)	27,000 (186.2)		

TECHNICAL DATA BULLETIN

GRADE: P95

NEMA LI 1-1998 Grade: --

U.L. LISTED: N

TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Thickness Tested		
		0.0625"	0.125"	0.500"
THERMAL PROPERTIES				
Temperature Index ¹ (UL Bulletin 746b) Electrical / Mechanical	°C	/ 200		
Coefficient of Thermal Expansion (IPC-TM 650-2.4.24) X-axis / Y-axis	" / °C x10 ⁻⁶	10.0 / 13.0		
Tg by DMA	°C	200		
Flammability Rating Condition A (UL Bulletin 94)	Class	HB		
ELECTRICAL PROPERTIES				
Dissipation Factor @ 1 MHz (ASTM D150)	Condition A	-		
	Condition D-24/23	-	0.010	
Relative Permittivity @ 1 MHz (ASTM D150)	Condition A	-		
	Condition D-24/23	-	4.80	
Breakdown Voltage (ASTM D149)	Condition A	kVolts	65	
	Condition D-48/50	kVolts	55	
Electric Strength (ASTM D149)	Condition A	Volts/mil (kV/cm)	850 (334.6)	
	Condition D-48/50	Volts/mil (kV/cm)	750 (295.3)	
Arc Resistance (ASTM D495)	Condition A	sec	130	
Comparative Tracking Index (ASTM D3638)		Volts	240	

¹ This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to check with Customer Service or, preferably our web site, www.norplex-micarta.com, to determine if the information is the most current available.

Specification writers: Contact Norplex-Micarta for specification values before submission.