

RM315 TECHNICAL DATA BULLETIN

GRADE: RM315 NEMA LI 1-1998 GRADE: -- U.L. LISTED: N

DESCRIPTION: Rolled and Molded Rods made from a plain weave, medium weight cotton fabric combined with a phenolic resin system to which graphite power has been added as a solid lubricant. RM315 is used for mechanical applications only, and should not be used in electrical applications. The applications for RM315 include bushings, bearings and push rods where external lubrication can not or is not provided.

TYPICAL PROPERTIES

		UNITS	VALUE ¹		
			Diameter Tested		
				0.500"	
PHYSICAL PROPERTIES					
Specific Gravity		-		1.35	
Rockwell Hardness		M Scale		90	
Moisture Absorption	Condition D ₁ -24/23	%		0.82	
Flexural Strength	Condition A	psi		18,500	
Tensile Strength	Condition A	psi		9,600	
Compressive Strength	Condition A	psi		28,400	
THERMAL PROPERTIES					
Temperature Index ²					
	Electrical / Mechanical	°C		115 / 125	
Flammability Rtg. (UL 94)	Condition A	Class		НВ	

¹ All testing performed to ASTM D-349 unless otherwise indicated.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to contact Customer Service, or preferably our web site, www.norplex-micarta.com, to determine if information is the most current. Specification writers: Contact Norplex-Micarta for specification values before submission.

² NEMA LI-6: This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.