

RT628H

TECHNICAL DATA BULLETIN

GRADE: RT628H

NEMA LI 1-1998 GRADE: XX

U.L. LISTED: N

DESCRIPTION: Being a heat treated version of RT628, RT628H is an improved machining grade meeting NEMA XX for tubes. It has low moisture absorption and good dimensional stability. Typical applications are as a replacement for RT629 where improved machining characteristics are needed. The primary application is in transformers. RT628 meets ANSI/NEMA IM 60000-2021 Grade XX and MIL-I-24768/11, PBG.

TYPICAL PROPERTIES

	UNITS	VALUE		
		Specimen Tested (ID x OD)		
			0.75" x 1.00"	
PHYSICAL PROPERTIES				
Specific Gravity (ASTM D792)	-		1.23	
Rockwell Hardness (ASTM D785)	M Scale		85	
Moisture Absorption Condition D ₁ -24/23 (ASTM D570)	%		1.30	
Acetone Extraction Condition A (ASTM F2953-12)	%		<1.0	
Compressive Strength Condition A (ASTM D695)	psi		19,000	
Compressive Modulus Condition A (ASTM D695)	kpsi		360	

RT628H - TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Specimen Tested (ID x OD)		
			0.75" x 1.00"	
THERMAL PROPERTIES				
Temperature Index ¹ Electrical / Mechanical	°C		130 / 130	
Flammability Rating Condition A (UL Bulletin 94)	Class		HB	
ELECTRICAL PROPERTIES				
Electric Strength (ASTM D149)	Condition A	Volts/mil	360	
	Condition D-48/50	Volts/mil	330	

¹ NEMA LI-6: This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to contact Customer Service, or preferably our web site, www.norplex-micarta.com, to determine if information is the most current.

Specification writers: Contact Norplex-Micarta for specification values before submission.