

# RT630H

## TECHNICAL DATA BULLETIN

**GRADE: RT630H**

**NEMA LI 1-1998 GRADE: XXX**

**U.L. LISTED: N**

DESCRIPTION: Being a heat treated version of RT630, RT630H is a fine machining grade with excellent electrical properties and moisture resistance. It has good dimensional stability and resists splitting. Typical applications include fuse tubes, coil forms and supports. RT630H meets ANSI/NEMA IM 60000-2021 Grade XXX and ASTM F2953.

### TYPICAL PROPERTIES

	UNITS	VALUE		
		Specimen Tested (ID x OD)		
			0.75" x 1.00"	
<b>PHYSICAL PROPERTIES</b>				
<b>Specific Gravity</b> (ASTM D792)	-		1.33	
<b>Rockwell Hardness</b> (ASTM D785)	M Scale		110	
<b>Moisture Absorption</b> Condition D <sub>1</sub> -24/23 (ASTM D570)	%		0.70	
<b>Tensile Strength</b> Condition A (ASTM D638)	psi		15,500	
<b>Compressive Strength</b> Condition A (ASTM D695)	psi		24,000	
<b>Compressive Modulus</b> Condition A (ASTM D695)	kpsi		375	

## RT630H - TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Specimen Tested (ID x OD)		
			0.75" x 1.00"	
<b>THERMAL PROPERTIES</b>				
<b>Temperature Index</b> <sup>1</sup> Electrical / Mechanical	°C		140 / 130	
<b>Flammability Rating</b> Condition A (UL Bulletin 94)	Class		HB	
<b>ELECTRICAL PROPERTIES</b>				
<b>Breakdown Voltage</b> Condition A (ASTM D149)	kVolts		80	
	Condition D-48/50	kVolts	29	
<b>Electric Strength</b> Condition A (ASTM D149)	Volts/mil		500	
	Condition D-48/50	Volts/mil	350	

<sup>1</sup> NEMA LI-6: This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to contact Customer Service, or preferably our web site, [www.norplex-micarta.com](http://www.norplex-micarta.com), to determine if information is the most current.

Specification writers: Contact Norplex-Micarta for specification values before submission.