

RTB326

TECHNICAL DATA BULLETIN

GRADE: RTB326

NEMA LI 1-1998 GRADE: --

U.L. LISTED: N

DESCRIPTION: Grade RTB326 is a tube made from a fine cotton fabric and an epoxy resin system. It has low moisture absorption and excellent dimensional stability and chemical resistance. Typical uses include bearing retainers and parts that require excellent machining characteristics. RTB326 meets ASTM F3131 Type FB.

TYPICAL PROPERTIES

	UNITS	VALUE		
		Specimen Tested (ID x OD)		
			0.75" x 1.00"	
PHYSICAL PROPERTIES				
Specific Gravity (ASTM D792)	-		1.33	
Rockwell Hardness (ASTM D785)	M Scale		110	
Moisture Absorption Condition D ₁ -24/23 (ASTM D570)	%		0.90	
Tensile Strength Condition A (ASTM D638)	psi		12,500	
Compressive Strength Condition A (ASTM D695)	psi		30,000	
Compressive Modulus Condition A (ASTM D695)	kpsi		470	

RTB326 - TYPICAL PROPERTIES (continued)

	UNITS	VALUE		
		Specimen Tested (ID x OD)		
			0.75" x 1.00"	
THERMAL PROPERTIES				
Temperature Index ¹ Electrical / Mechanical	°C		140 / 140	
Flammability Rating Condition A (UL Bulletin 94)	Class		HB	
ELECTRICAL PROPERTIES				
Breakdown Voltage Condition A (ASTM D149)	kVolts		75	
	Condition D-48/50	kVolts	30	
Electric Strength Condition A (ASTM D149)	Volts/mil		350	
	Condition D-48/50	Volts/mil	300	

¹ NEMA LI-6: This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to contact Customer Service, or preferably our web site, www.norplex-micarta.com, to determine if information is the most current.

Specification writers: Contact Norplex-Micarta for specification values before submission.