



Global Thermoset Composite Solutions

BT25NEE

TECHNICAL DATA BULLETIN

GRADE: BT25NEE

NEMA GRADE: --

U.L. LISTED: N

DESCRIPTION: Grade BT25NEE is a tube made from a fine cotton fabric and an epoxy resin system. It has low moisture absorption and excellent dimensional stability and chemical resistance. Typical uses include bearing retainers and parts that require excellent machining characteristics.

TYPICAL PROPERTIES

	UNITS	VALUE		
		Specimen Tested (ID x OD)		
			0.75" x 1.00"	
PHYSICAL PROPERTIES				
Specific Gravity (ASTM D792)	-		1.33	
Rockwell Hardness (ASTM D785)	M Scale		110	
Moisture Absorption (ASTM D570)	Condition D ₁ -24/23	%	0.90	
	Condition E-24/50	%		
Acetone Extraction (ASTM F2953-12)	Condition A	%		
Tensile Strength (ASTM D638)	Condition A	psi	12,500	
	Condition E-1/150: T-150	psi		
Tensile Modulus (ASTM D638)	Condition A	kpsi		
	Condition E-1/150: T-150	kpsi		
Compressive Strength (ASTM D695)	Condition A	psi	30,000	
	Condition E-1/150: T-150	psi		
Compressive Modulus (ASTM D695)	Condition A	kpsi	470	
	Condition E-1/150: T-150	kpsi		

BT25NEE - TYPICAL PROPERTIES (continued)

		UNITS	VALUE		
			Specimen Tested (ID x OD)		
				0.75" x 1.00"	
THERMAL PROPERTIES					
Temperature Index ¹	Electrical / Mechanical	°C		140 / 140	
Tg by DMA	Condition A	°C			
Flammability Rating (UL Bulletin 94)	Condition A	Class		HB	
ELECTRICAL PROPERTIES					
Dissipation Factor @ 1 MHz (ASTM D150)	Condition A	-			
	Condition D-24/23	-			
	Condition D-48/50	-			
Relative Permittivity @ 1 MHz (ASTM D150)	Condition A	-			
	Condition D-24/23	-			
	Condition D-48/50	-			
Breakdown Voltage (ASTM D149)	Condition A	kVolts		75	
	Condition D-336/50	kVolts			
	Condition D-48/50	kVolts		30	
Electric Strength (ASTM D149)	Condition A	Volts/mil		350	
	Condition D-48/50	Volts/mil		300	

¹ NEMA LI-6: This temperature is a recommendation only, and based upon experience in various applications. The maximum operating temperature is dependent upon the application and should be investigated prior to use.

This data, while believed to be accurate and based on reliable analytical methods, is for informational purposes only. The terms and conditions of the agreement under which it is sold will govern any sales of this product. Data supplied above are "typical values"; not to be considered "specification values".

To assure the material's performance is adequate for a specific application; customers should verify, independent of Norplex-Micarta, performance characteristics of interest.

It is the responsibility of the users of this information to make sure that they have the latest version of this TDB, and are urged to contact Customer Service, or preferably our web site, www.norplex-micarta.com, to determine if information is the most current.

Specification writers: Contact Norplex-Micarta for specification values before submission.